



LB THERM GLUE-XPS-GLUE



COMPOSITION: GLUE|XPS|GLUE

EXTERNAL LAYER:

Glue secured with a silicone paper.

CORE:

XPS - extruded polystyrene

- Fire resistance: E class acc. to EN 13501-1
- Thermal conductivity rate – 0,034 W/(m*K)
- XPS – DIN EN13164-T3-CS(10\Y)200-DS(70,90)-DLT(2)7-TR600-MU50

Thickness	[mm]	8	10	16	18	20	22	24	26	28	30
Wartość U*	$\left[\frac{W}{m^2K}\right]$	2,46	2,15	1,56	1,43	1,32	1,22	1,14	1,07	1,01	0,95

*Heat transmission rate has been determined by a calculation method

Thickness	[mm]	32	34	36	38	40	42	44	46	48	50
Wartość U*	$\left[\frac{W}{m^2K}\right]$	0,9	0,85	0,81	0,77	0,74	0,71	0,68	0,65	0,63	0,6

*Heat transmission rate has been determined by a calculation method

AVAILABLE SIZES [mm]: 3000x1000